Adhesives





General Properties:

- TILEX is cement base adhesive, ready mix dry mortar just add water, used for fixing tiles, ceramic, marble on cement substrata as concrete, plaster, screed & the like.
- Non-sag mortar after mixing & can be used on verticals, soffits & floors.
- Long pot life to enable the labor proper time to fix up tiles.
- Excellent adhesion to surfaces.

Substrate:

- Substrate should be sound.
- Substrate should be clean, free from dust, oil, grease or any other foreign materials.
- Wet substrate & tiles with water before application.

Application:

- 1. Put 4.30 liters of water in a large vessel and add 25 kg of , mix mechanically or manually.
- 2. Leave for 5 minutes then repeat mixing again, add water if required.
- 3. TILEX is to be applied with thickness from 2mm 4mm to the surface with a notched trowel (ensure that the thickness of the layer is appropriate to the tile dimensions and roughness of substrate).
- 4. Twist while pressing the tile into substrate till maximum adhesion is achieved.
- 5. Using temporary plastic support (spacers).
- 6. Remove excess **TILEX** using a wet sponge.
- 7. Clean joints to be ready for accepting its grouting mortar.
- 8. Clean tools immediately after application using water.

Technical Data:

: 290 kg/cm² (after 7 days) ASTM C 109/109M. Compressive strength

Color : Dark gray and white. Water ratio : 17.5 % by weight .

: 1.8 kg/1 m² / 1mm thick depends on substrate and tile dimensions. Consumption

Packaging : 5 kg, 25 kg.

Shelf Life : 12 months in original bags away from sun light and humidity.

Environment:

- **TILEX** non-toxic suitable to use in potable water structures.
- Boots, rubber gloves, dust masks, and safety goggles.
- Refer to MATERIAL SAFETY DATA SHEETS (MSDS)

END OF TECHNICAL DATA

For more information please contact our technical department

Head Office: 21 Takseem El Awkaf – EL Sawah Sq. Cairo – Egypt Tel: 002 / 02 24535678 - 24535679 Fax: 002 / 02 24538986 Web site: www.yasmomisr.com E-mail: yasmo@yasmomisr.com









28437/B

28437/C