

Mortars

DECORENDER

Non-Sag Mortar For Vertical Stamped Concrete

**General Properties:**

- **DECORENDER** is one component, ready mix dry mortar used for applying vertical stamped layer on cement substrata as concrete, plaster and bricks.
- Non-sag mortar after mixing & can be used on verticals, soffits.
- Long pot life to enable the labor to stamp it.
- Excellent adhesion to surfaces.
- Give a very smooth surface which is similar to natural stone free of cracks.
- Can be applied up to 3 cm thickness one shot.
- Compressive strength 100 kg/cm² after 7 days.
- Endures weathering conditions.

Preparation of Surface:

- Substrate should be sound.
- The substrate should be clean, free from dust, oil, grease or any other foreign materials.
- In case the surface is fare face concrete,
 - Prime with **VERSASEAL**.
 - Splash the substrata using **C-LATEX** with water (1:3) mixed with (1 cement: 3 sand) to make slurry, to be applied before 24 hours at least of applying **DECORENDER**.

Application:

1. Put 0.8 liters of water in a large vessel and add 10 kg **DECORENDER**, mix mechanically or manually, leave for 5 minutes then repeat mixing.
2. **DECORENDER** is to be applied as a layer with thickness up to 3 cm by using trowel (insure that the thickness of the **DECORENDER** layer is suitable to the stamp you are using).
3. Spray the release agent on the mortar before stamping to avoid sticking of the stamp to the mortar.
4. Start stamping the mortar within maximum 40 minutes.
5. Using a wet brush, fix deteriorated areas.
6. Clean tools immediately after application using water.
7. For repairing after setting of the mortar use **CRETEREP V.P.**

Technical Data:

| | |
|-----------------------------|---|
| Compressive strength | : 100 kg/cm ² after 7 days ASTM C-109/109M |
| Water ratio | : 29 % by weight from powder |
| Pot life | : 40 minute |
| Shelf Life | : 12 months in closed container away from direct sunlight, heat and humidity. |

Environment:

- Boots, rubber gloves, dust masks, and safety goggles.
- Refer to MATERIAL SAFETY DATA SHEETS (MSDS)

For more information please contact our technical department

Head Office: 21 Takseem El Awkaf – EL Sawah Sq. Cairo – Egypt
 Tel: 002 / 02 24030678 – 24030679 Fax: 002 / 02 24038986
 Web site: www.yasmomiser.com E-mail: yasmo@yasmomiser.com