



### General Properties:

- **GYPCOAT** is ready mix modified fine gypsum, enables users to achieve a very high standard finishing. When using it as a single final coat over smooth or rough substrata.
- Initial setting time reaches from ٥٠ - ٦٠ minutes that enables the workers to produce high quality finishing.
- Excellent adhesion to substrate.
- Water ratio ٤٠% that provides high strength of **GYPCOAT**.
- Thickness of final finish coat ranges from ٢ mm to ١٠ mm. and can be applied by machine gun.

### Substrate:

- All cement substrate.
- All kinds of bricks and stones.

### Uses:

- Final plaster one shot for Fair face concrete.
- Interior finishing.
- Repairing to plaster.
- As bonding agent for fiber glass tissue.

### Application:

١. Clean substrate well, and wet with water especially in summer.
٢. Pour water in a wide vessel then add **GYPCOAT** gradually then mix well manually or by a mechanical mixer
٣. Apply **GYPCOAT** using a stainless steel trowel with a thickness not more than ١٠mm.

**Note:** The temperature of substrate should not exceed ٣٠°C during application & it is recommended to damp the surface using water, especially in summer.

### Technical Data:

<b>Color</b>	: White powder.
<b>Compressive Strength</b>	: ٦٠ kg / cm <sup>٢</sup>
<b>Thickness</b>	: From ٢ mm up to ١٠ mm.
<b>Coverage</b>	: ١ kg covers ١ m <sup>٢</sup> for thickness ١ mm.
<b>Environment</b>	: Friendly
<b>Setting Time</b>	: ٥٠-٦٠ minutes
<b>Water Ratio</b>	: About ٠.٤ liter / kg <b>GYPCOAT</b>
<b>Shelf Life</b>	: ١٢ months in closed container and away from sunlight, heat and humidity.

**Environment:** - Boots, rubber gloves, dust masks, and safety goggles.  
- Refer to MATERIAL SAFETY DATA SHEETS (MSDS)

**For more information please contact our technical department**

Head Office: ٢١ Takseem El Awkaf – EL Sawah Sq. Cairo – Egypt  
Tel: ٠٠٢ / ٠٢ ٢٤٥٣٥٦٧٨ – ٢٤٥٣٥٦٧٩ Fax: ٠٠٢ / ٠٢ ٢٤٥٣٨٩٨٦  
Web site: [www.yasmomiser.com](http://www.yasmomiser.com) E-mail: [yasmo@yasmomiser.com](mailto:yasmo@yasmomiser.com)