

Finishing

MISRMIX

Decorative Dry Mortar



General Properties:

- **MISRMIX** is cement base, dry mix mortar formulated for external & internal finishing.
- Supplied in different colors.
- Easy for application.
- Provides saving of cost & time.
- High labor productivity.
- Excellent **cohesion & adhesion**.
- Gives high desirable textures.
- The product has relative specifications compatible to cement substrate.

Application:

1. Clean the surface from loose particle, oil, grease, or any foreign materials.
2. Surface should be wetted before applying **MISRMIX**.
3. Repair all cracks before application using **Creterep 30**.
4. Put the water (6 liters / 20 kg powder) in a suitable container, and then add **MISRMIX** gradually.
5. Mix well for at least 3 min., leave for 25 min. and repeat mixing.(mechanical mixing).
6. Mix only the quantities required for application within 45 min.
7. Apply **MISRMIX** with steel trowel with proper thickness, and then leave to dry (neither wetted spots nor glossy surface).
8. Spray water over **MISRMIX** as this can help in final finishing.
9. Rub the surface (finishing) with a sponge or wooden rough tool.

Important Notes:

- The temperature of substrate should not exceed 30C during application & it is recommended to damp the surface using water, especially in summer.
- The ratio of water should be fixed for every plastic bag to maintain the homogeneity of color.
- In case of using mechanical mixer: mix with low speed for 3 min and then leave for 5 min then remix.
- In case of manual mixing: mix for 5 min then leave for 25 min and then remix for 5 min.

Technical Data:

Binder	: Hydraulic & Synthetic resins.
Water Ratio	: 30% form powder (by Wight).
Consistency	: Dry mix.
Consumption	: 1.5 kg / 1 mm thickness / 1m ² .
Layer Thickness	: 1.5 - 5 mm.
Pot Life	: 45 minutes after mixing.
Adhesion Strength	: > 1 N / mm ² on cement substrate (Din18555/6) (EN 1348).
Abrasion	: 120 mg (1000 cycle – 1000 gm weight).
Shelf Life	: 12 months in closed container and away from sunlight, heat and humidity.

Environment: - Boots, rubber gloves, dust masks, and safety goggles.
- Refer to MATERIAL SAFETY DATA SHEETS (MSDS)

For more information please contact our technical department

Head Office: 21 Takseem El Awkaf – EL Sawah Sq. Cairo – Egypt
Tel: 002 / 02 24535678 - 24535679 Fax: 002 / 02 24538986
Web site: www.yasmomisr.com E-mail: yasmo@yasmomisr.com