

**General Properties:**

- **CURETE** is an acrylic base Liquid curing and concrete surface hardener mainly forming non porous solid membrane on concrete surface.
- Distinguished with its high penetrating depth through porous substrata.
- Strongly reduces absorption property of substrate.
- Prevents evaporation of water in cement mix specially during setting time of concrete.
- Prevents cracks created from shrinkage due to evaporation of cement mixing excess water.
- Increases abrasion resistance to concrete surfaces.
- Has excellent adhesion to concrete surface.
- Gives non porous surface and dust repellent surface.

Uses:

- 1- Curing and hardening of concrete floorings surface especially in hot or windy weather and areas where is rare.
- 2- Curing and hardening of concrete forms after casting
- 3- Curing and hardening of screeds especially small thickness.

Applications:

1. Mix **CURETE** well in container before application.
2. Dilute curate 25% with water.
3. **Apply CURETE** from 8 – 10 hours after casting or after releasing forms.
4. In case of flooring The suitable time to apply **CURETE** is when the appearance of the casted concrete surface changes from shiny to dull and hard enough for stepping on. Time depends on the water\cement ratio & temperature.
5. **CURETE** can be applied by one of the following tools :
 - Spraying tool.
 - Roller.
 - Brush.

Technical Data:

Bonding Agent	: Synthetic acrylic polymer .
Color	: Milky . clear on drying
Form	: Liquid.
Dilution	: Water.
Density	: 1.05 Kg / liter.
Environment	: Friendly .
Consumption	: 100 - 150 gm / m ² .
Ph	: 8
Containers	: 5 kg, 20 Kg . 100 kg
Shelf Life	: 12 months in closed container away from direct sunlight and humidity.

Environment:

- Boots, rubber gloves, dust masks, and safety goggles.
- Refer to MATERIAL SAFETY DATA SHEETS (MSDS)

For more information please contact our technical department

Head Office : 21 Takseem El Awkaf – EL Sawah Sq. Cairo – Egypt
 Tel : 002 / 02 24535678 - 24535679 Fax : 002 / 02 24538986
 Web site : www.yasmomiser.com E-mail: yasmo@yasmomiser.com



28437/A



28437/B



28437/C



Concrete
Additives

CURETE

Liquid curing and concrete surface hardener



END OF TECHNICAL DATA

For more information please contact our technical department

Head Office : 21 Takseem El Awkaf – EL Sawah Sq. Cairo – Egypt
Tel : 002 / 02 24535678 - 24535679 Fax : 002 / 02 24538986
Web site : www.yasmomISR.com E-mail: yasmo@yasmomISR.com



28437/A



28437/B



28437/C

